

**PRODUCT INFORMATION**  
**OKULEN® 1000 Reg.-multi coloured-FN9005**

OKULEN® 1000-Reg. (PE-UHMW)

Ultra high molecular weight low pressure polyethylene with regenerated (recycled) materials.

Colour: black multi-coloured FN9005

## Characteristics and standard values

Properties	Method	OKULEN® 1000 Reg.-multi coloured-FN9005	
		SI	US
<b>Physical properties</b>			
Molecular-weight	k.a.	> 2.0 Mio. g/mol.	> 2.0 Mio. g/mol.
Density	DINENISO 1183-1 (09/2019) ASTM D792	> 0.940 g/cm <sup>3</sup>	> 58.682 lb/ft <sup>3</sup>
Notched impact strength	DINENISO 21304-2 (04/2021)	> 30 kJ/m <sup>2</sup>	> 14.265 ft-lb/in <sup>2</sup>
Abrasion-Index (Sand-Slurry)	DINENISO 15527 (05/2022)	130 - 250	130 - 250
Tensile strength at yield (1B - 50mm/Min.)	DINENISO 527-2 (06/2012) ASTM D 638 (2010)	> 20 N/mm <sup>2</sup>	> 2900 psi
	---	---	---
Elongation (Break / 1B - 50mm/Min.)	DINENISO 527-2 (06/2012) ASTM D 638 (2010)	> 150 %	> 150 %
Tensile-E-modulus (1B - 1mm/Min.)	DINENISO 527-2 (06/2012) ASTM D 638 (2010)	> 700 N/mm <sup>2</sup>	> 101500 psi
	---	---	---
Static Friction	ASTM D 1894 (2014)	~ 0.16 - 0.22	~ 0.16 - 0.22
Dynamic Friction	ASTM D 1894 (2014)	~ 0.10 - 0.17	~ 0.10 - 0.17
Shore-D-Hardness, 3 sec. value 6 mm plate	DINENISO 868 (10/2003)	64 - 68 D	64 - 68 D
Ball indentation hardness	DINENISO 2039	38 N/mm <sup>2</sup>	5510 psi
Water absorption	DINENISO 62 (05/2008)	< 0.01 %	< 0.01 %
<b>Thermal properties</b>			
Melting Point (DSC)	DINENISO 11357-1 (03/2010)	133 - 137 °C	271.4 - 278.6 °F
Thermal Conductivity	Wire method	~ 0.41 W/m*K	~ 2.84253 (BTU-in)/hr-ft <sup>2</sup> -°F
Max. operation temperature	Literature	80 °C	176 °F
Coefficient of thermal expansion (23 - 80°C)	ISO 11359	~ 0.00020 mm/mm °C	~ 0.000111 in/in °F
<b>Electrical properties</b>			
Volume resistivity	DINEN 62631-3-1 (01/2017)	< 1.0E+14 Ohm*cm	< 1.0E+14 Ohm*cm
Surface resistivity	DINEN 62631-3-2 (10/2016)	< 1.0E+13 Ohm	< 1.0E+13 Ohm
ATEX-Directive - TÜV approved!	ATEX-Directive	---	---
ESD-D	---	--- Ohm	--- Ohm
<b>Burning properties</b>			
Fire resistance (Self-classification)	DIN 4102	B2 Klasse	B2 Class
Fire resistance (Self-classification)	UL94	HB Klasse	HB Class
<b>Physiological properties</b>			
Food compliant		---	---

**Ottensteiner Kunststoff GmbH & Co. KG**

Im Garbrock 39, 48683 Ahaus-Ottenstein Germany

Phone: +49 (0) 2561-9824-0

Internet: [www.okulen.com](http://www.okulen.com)

e-mail: [info@okulen.com](mailto:info@okulen.com)