

PRODUCT INFORMATION
OKULEN® 2000 - Certec - FN1450

OKULEN® 2000 - Certec - FN1450 is a special UHMW-PE Polymer-compound (7 - 9 Mio. g/mol). With this special fillers we reach a very high up to extremely high wear resistance and excellent sliding properties.

Properties:

- extremely wear resistant,
- good sliding properties,
- good chemical resistance

Colour:

pearl white FN1450 / similar RAL1013

Range of applications:

Paper industry (High-Tech-Paper-Machines)

PRODUCT INFORMATION

OKULEN® 2000 - Certec - FN1450

Characteristics and standard values

Properties	Method	OKULEN® 2000 - Certec - FN1450	
		SI	US
Physical properties			
Molecular-weight	k.a.	7.0 - 9.0 Mio. g/mol.	7.0 - 9.0 Mio. g/mol.
Density	DINENISO 1183-1 (09/2019) ASTM D792	> 1.010 g/cm³	> 63.052 lb/ft³
Notched impact strength	DINENISO 21304-2 (04/2021)	> 70 kJ/m²	> 33.285 ft-lb/in²
Abrasion-Index (Sand-Slurry)	DINENISO 15527 (05/2022)	70	70
Tensile strength at yield (1B - 50mm/Min.)	DINENISO 527-2 (06/2012) ASTM D 638 (2010)	> 17 N/mm²	> 2465 psi
	---	---	---
Elongation (Break / 1B - 50mm/Min.)	DINENISO 527-2 (06/2012) ASTM D 638 (2010)	> 50 %	> 50 %
Tensile-E-modulus (1B - 1mm/Min.)	DINENISO 527-2 (06/2012) ASTM D 638 (2010)	> 700 N/mm²	> 101500 psi
	---	---	---
Static Friction	ASTM D 1894 (2014)	~ 0.16	~ 0.16
Dynamic Friction	ASTM D 1894 (2014)	~ 0.12	~ 0.12
Shore-D-Hardness, 3 sec. value 6 mm plate	DINENISO 868 (10/2003)	65 - 67 D	65 - 67 D
Ball indentation hardness	DINENISO 2039	--- N/mm²	--- psi
Water absorption	DINENISO 62 (05/2008)	< 0.01 %	< 0.01 %
Thermal properties			
Melting Point (DSC)	DINENISO 11357-1 (03/2010)	135 - 137 °C	275 - 278.6 °F
Thermal Conductivity	Wire method	--- W/m*K	--- (BTU-in)/hr-ft²-°F
Max. operation temperature	Literature	~ 80 °C	~ 176 °F
Coefficient of thermal expansion (23 - 80°C)	ISO 11359	~ 0.00015 - 0.00020 mm/mm °C	~ 0.000083 - 0.000111 in/in °F
Electrical properties			
Volume resistivity	DINEN 62631-3-1 (01/2017)	> 1.0E14 Ohm*cm	> 1.0E14 Ohm*cm
Surface resistivity	DINEN 62631-3-2 (10/2016)	> 1.0E13 Ohm	> 1.0E13 Ohm
ATEX-Directive - TÜV approved!	ATEX-Directive	---	---
ESD-D	---	--- Ohm	--- Ohm
Burning properties			
Fire resistance (Self-classification)	DIN 4102	B2 Klasse	B2 Class
Fire resistance (Self-classification)	UL94	HB Klasse	HB Class
Physiological properties			
Food compliant		---	---

The above data are based on the present knowledge and are given without guarantee. Existing laws and conditions are to be respected by the user of our products. The decision about the suitability of a material for a certain application must be made by the user. We reserve the right to alter the indicated data. The indicated values are for a 15 mm thick sheet, unannealed. Black sheets may have antistatic properties.

Ottensteiner Kunststoff GmbH & Co. KG

Im Garbrock 39, 48683 Ahaus-Ottenstein
Germany

Phone: +49 (0) 2561-9824-0

Internet: www.okulen.com

e-mail: info@okulen.com